

APPENDIX TO REPORT OF

LIST of NAMES—continued.

Name.	District and Authority.			Remarks.
<i>Ngaro</i> ...	Taranaki, Kelly ...	...	...	Used for rough garments.
	Waikato, Jenkins ...	...	...	Good fibre; blueish green leaf; black edge.
	Raglan, Snackenburg... ..	...	...	Best of all the kinds, for all purposes.
	West Coast, Heaphy ...	...	...	Stiff fibre.
<i>Ngarowaka</i> ...	Waikato, Jenkins ...	...	...	Good fibre for mill purposes; leaf, bright green; red edge.
	Waiuku, Constable ...	...	...	Cultivated; soft, fine fibre.
<i>Ngatotomawe</i> ...	Opunake, Native ...	...	...	Breaking strain, 84.
<i>Ngutunui</i> ...	Taranaki, Kelly ...	...	...	For best garments; quick grower; leaf similar to <i>Takaiapu</i> , but has a blunt point, and is red at the butts.
	Opunake, Native ...	...	...	Breaking strain, 95.
	Waikanae, Wi Tako ...	...	...	Much esteemed leaf; dark olive green, with dark red edge.
	West Coast, Heaphy ...	...	...	
<i>Ngutuparera</i> ...	Taranaki, Kelly ...	...	...	For rough garments.
	Opunake, Native ...	...	...	<i>Parera</i> (?). Breaking strain, 95.
	West Coast, Heaphy ...	...	...	or <i>Ngutuparura</i> (?).
<i>Oka Oka</i> ...	Waiuku, Constable ...	...	...	One of the best varieties; cultivated.
<i>Oue</i> ...	Christchurch Domain, Armstrong			Leaf, narrow, very strong; edges, orange coloured; per centage of fibre, 34.1.
	Taranaki, Kelly ...	...	...	Leaf narrow, of an olive green; edge and keel, orange coloured; used for best garments.
	Hawke's Bay, Locke ...	...	...	Fine fibre, next to <i>Tapoto</i> .
	Whakatane, Native ...	...	...	Best variety, white and soft. Breaking strain, 91.
	Waikato, Hutton ...	...	...	Typical <i>Tihore</i> .
	Ditto Mantell ...	...	...	A fine fibre. Also, <i>Ouhe</i> .
	East Coast, Heaphy ...	...	...	Also, <i>Tapoto</i> , cultivated at Coromandel, Kawhia, and Waikato; glossy leaves, rather red at the edge; has a general orange-green appearance at a distance.
	Maungatautari, Bishop Selwyn...			<i>Tihore</i> .
<i>Paheke</i> ...	Opunake, Native ...	...	...	Breaking strain, 87.
<i>Parekoritawa</i> ...	Taranaki, Kelly ...	...	...	Variegated variety; leaf, very bright green longitudinal stripe, of brimstone colour; fibre very good; edge and keel orange colour.
	Opunake, Native ...	...	...	Breaking strain, 79.
	Waitara, Woon ...	...	...	Very white, and strong fibre.
	West Coast, Heaphy ...	...	...	Yields best fibre.
	Christchurch, Armstrong			Per centage of fibre, 18.8.
<i>Paretaniwha</i> ...	Whakatane, Native ...	...	...	Strong fibre for fishing lines, nets, &c. Breaking strain, 95.
	Opunake, Native ...	...	...	Breaking strain, 83.
	Maungatautari, Bishop Selwyn...			A <i>Tihore</i> .
	Ditto Mantell ...	...	...	Fine kind.
	Waikato, Hutton ...	...	...	Yellow, hill flax. Strip of leaf $\frac{1}{8}$ inch broad, broke at 42 lbs.
<i>Pato</i> ...	Taranaki, Kelly ...	...	...	Used for rough purposes.
	West Coast, Heaphy ...	...	...	Stiff fibre.
<i>Poitaniwha</i> and	Waikato, Jenkins ...	...	...	or <i>Paretaniwha</i> (?)—Good fibre for mill purposes; dark green leaf.
<i>Ngutukaka</i>				
<i>Papu</i> ...	Waikato, Jenkins ...	...	...	Yellowish-green; brown butts, red edge. Good fibre for mill purposes.
<i>Rataroa</i> ...	Taranaki, Kelly ...	...	...	Said to be used for best purposes. Taper, acuminate, bronzy, green leaf; dark purple keel and edge, fading on the upper side.
	Waiuku, Constable ...	...	...	Best <i>Tihore</i> ; varies from 3 to 8 feet, according to soil; red edge.
	St. John's College, from East Cape			The strongest of all the fibres. Breaking strain, 117.
	Christchurch, Armstrong ...	...	...	Per centage of fibre, 21.6.
	Waikanae, Native ...	...	...	Scarce. Very taper, light yellowish green leaf; narrow, dark edge.
<i>Ratawa</i> ...	Hauraki, Thames, Bishop Selwyn			A <i>Tihore</i> . Probably misprinted for <i>Rataroa</i> .
<i>Raumoa</i> ...	Taranaki, Kelly ...	...	...	Used for rough garments; light green leaf, reddish brown keel and edge; narrower underneath.
	Opunake, Native ...	...	...	Breaking strain, 76.