

LIST of NAMES—continued.

Name.	District and Authority.	Remarks.
<i>Raumoa</i> ...	Waikanae, Native ...	Darkish green leaf; broad, red-brown edge on upper side, narrow do. below.
<i>Rerehape</i> ...	Taranaki, Bishop Selwyn ...	<i>Raro</i> . Requiring to be scraped with a shell.
	West Coast, Heaphy ...	Yields best fibre; good for cordage.
<i>Rongotinui</i> ...	Maungatautari, Bishop Selwyn ...	A <i>Tihore</i> .
	Mantell ...	Fine kind.
<i>Tihore</i> ...	East Coast and Bay of Plenty ...	Used for fishing nets, and cordage; best fibre for mill purposes.
	Heaphy ...	Light green leaf, with wide black edge.
<i>Takaiapu</i> ...	Taranaki, Kelly ...	Breaking strain, 95.
(<i>Kiapu</i>) ...	Opunake, Native ...	Fibre very strong; leaf erect, brown edge.
	Taranaki, Kelly ...	Breaking strain, 76.
<i>Tapoto</i> ...	Opunake, Native ...	First-rate quality.
	Hursthouse ...	Leaves narrow, erect, deep purple margin; strong, lustrous fibre, used for sewing threads or weft of fine mats.
	Hawkes Bay, Nairn ...	Sometimes called <i>Tihore</i> or <i>Takiri</i> ; best variety.
	do. do. Locke ...	Also, <i>Oue</i> —fibre, glossy, silky, but brittle, used for <i>Kaitaka</i> mats.
	East Coast, Heaphy ...	Breaking strain, 101. 205574
	Opunake, Native ...	Similar to <i>Tihore</i> . Per centage of fibre, 18.7
	Christchurch, Armstrong ...	tapering at the points; edges red.
<i>Tarariki</i> ...	Taranaki, Kelly ...	Used for rough purposes.
	Opunake, Native ...	Breaking strain, 70.
	West Coast, Heaphy ...	Stiff fibre.
	Wanganui, Woon ...	Fine and soft texture, used for <i>Potas</i> , or ornamented mats; tapering acuminate leaves; dull, olive green, lighter on the outer side; dark red keel and edge, and keel on the upper side gradually shaded away, forming a dark coloured band $\frac{1}{2}$ to $\frac{3}{4}$ of an inch broad; 2 or 3 inches of the point of the leaves of the same dark colour.
<i>Tawai kakako</i> ...	Napier, Native ...	Dark colour when first scraped, but it is put into baskets, and kept to improve its colour.
<i>Tiheru</i> ...	Opunake, Native ...	Breaking strain, 98.
<i>Taihore</i> ...	Taranaki, Kelly ...	Plant or variety?
	Christchurch, Armstrong ...	Leaves linear; very strong; dark red edge. Per centage of fibre, 19.8.
	Raglan, Native ...	Breaking strain, 99.
	West Coast, Heaphy ...	Best fibre.
	Waikato, Hutton ...	Best variety, cultivated. Strip of leaf $\frac{1}{8}$ inch broad, bore a strain of 48 lbs.
<i>Tipuna</i> ...	Taranaki, Kelly ...	Used for rough garments.
	Hursthouse ...	<i>Tepuna</i> (?)
<i>Tito-o-moe-wai</i> ...	Taranaki, Kelly ...	Used for rough garments.
<i>Tuau</i> ...	Waikanae ...	Coarse plant, not used for fine work.
<i>Tuawhitu</i> ...	Bay of Islands ...	Fine and soft fibre. Leaf tapering, thin texture, bronzy colour, lined and smeared at the upper end, narrow, dark red edge.
<i>Tumara</i> ...	Waikato, Jenkins ...	Good fibre for mill purposes.
<i>Turepo</i> ...	Waikanae ...	Small yellow variety, grows in wet swamps, and has a white silky fibre; brown edge and keel.
<i>Tutaiwiki</i> ...	Taranaki, Hursthouse ...	Also, <i>Mangaeka</i> —Fibre of ordinary character.
<i>Wararika</i> ...	East Coast, Heaphy ...	Soft fibre, used for fine mats.
<i>Wharanui</i> ...	Hawke's Bay, Nairn ...	Next to <i>Oue</i> .
	do. do. Locke ...	Or <i>Wharanui</i> (?)
	Mantell ...	Weak fibre, only used for kits, &c.; very broad and tall leaf; grows in richest soils.
<i>Wharariki</i> ...	Hawkes Bay, Nairn ...	Used for rough garments.
<i>Phormium</i> ...	Taranaki, Kelly ...	Never used.
<i>Colensoi</i> ...	Waikanae, Native ...	Stiff fibre.
	Heaphy ...	Also, <i>Wharaeki</i> .
	Mantell ...	<i>Whararipi</i> .
	Bishop Selwyn ...	Strip of leaf $\frac{1}{8}$ inch broad; broke at 34 lbs.
	Waikato, Hutton ...	Poor fibre.
<i>Witau</i> ...	East Coast, Heaphy ...	