

No. I.—*Winsey*.—*Character* : Very harsh and strong, thick, wears well, warp of cotton, weft of wool (shoddy), staple 1 to 2 inches.

Wool per cent.	...	...	...	...	...	...	66·98
Cotton „	...	...	...	...	...	...	33·02

100·

No. II.—*Winsey*.—*Character* : Thin, harsh, strong. Dark and purple parts of weft was of wool, the rest cotton.

Wool per cent.	...	...	...	...	...	...	52·1
Cotton „	...	...	...	...	...	...	47·9

100·

No. III.—*Winsey*.—*Character* : Soft, smooth, thin. Warp of cotton, weft of wool.

Wool per cent.	...	...	...	...	...	...	69·4
Cotton „	...	...	...	...	...	...	30·6

100·

No. IV.—*Shally*.—Firm and harsh to the touch, variously coloured. Warp is composed of 45 per cent. cotton, 5·5 per cent. wool. Weft is all wool, and amounts to 49·5 per cent.

No. V.—*Shally*.—Same character as above. Warp is black and white cotton. Weft is wool.

No. VI.—Lustrous and strong. Warp of white silk, alternating with narrow stripes of black cotton. Weft is of wool. Colour purple.

WILLIAM SKEY,
Analyst.

By Authority; GEORGE DINSBURY, Government Printer, Wellington.—1873.

Price 6d.