No. 2.—RETURN of DEFECTS—continued.

No. 2.—RETURN Of DEFECTS—continued.						
Description of De	fects.		İ	Dangerous.	Defective in Lesser Degree.	Total
er enemer er			,	•		
Crown of boiler wasted		•••		•••	2	2
Crown of firebox badly bulged	•••	•••		3	9	12
Crown of firebox corroded				2	8	10
Crown of firebox cracked	•••	• • •		•••	2	2
Crown of firebox laminated	•••	• • • •	• • •	•••	2	2
Crown of firebox slightly bulged Crown of firebox wasted (pressure	 reduced	٠		•••	11	11
Crown of steam-dome wasted	···	•	• • •	•••	3 2	$egin{array}{c} 3 \\ 2 \end{array}$
Crown stays defective	•••		•••	•••	2	2
Crown stay-nuts defective			•••	•••	1 1	1
Defective dogs on manhole-doors	•••			•••	3	3
Eight screwed stays in firebox bad	1			•••	3	3
Eight tubes bad					1	1
Eighteen rivets in front tube-plate		• • •	• • •		1	1
Eighteen screwed stays in firebox	bad		• • • •	•••	3	3
Eighteen tubes bad	•••		• • •	•••	1	1
Fifty three growed stays in free	 w had	•••	•••		1	1
Fifty-three screwed stays in firebox) Χ. D&O. n. n.u1		 	1	•••	1
Firebox badly bulged on sides and stays bad	t a numbe	er or scre	wed	2		2
Firebox general waste	•••	•••		3	8	11
Firebox-sides bulged	•••	•••			4	4
Firebox thin round bottom		• • •		1		1
Firebox tube-plate cracked and tu		•••	•••	1	•	1
Five longitudinal stays bad		• • •		• • •	1	1
Five tubes bad	• • •	• •	• • •	•••	4	4
Flanging of boiler defective	• • •	•••	• • •	• • •	1	1
Flue-end defective	frohen d		• • •	• • •	1	1
Foundation-rings round bottom of Forty-four screwed stays in firebox			• • •		10	10
Forty-three screwed stays in firebo		• • •	• • •	1 1	•••	1
Four mudhole-doors bad		• • •	• • •	_	ï	1
Four screwed stays in firebox bad					5	1 5
Four stay-tubes bad				•••	1	1
Four tubes bad	•••			•••	$\frac{1}{2}$	$\overset{1}{2}$
Four vertical stays defective				•••	$\bar{1}$	ĩ
Front tube-plate wasted				•••	<u>-</u> 6	6
Furnaces bad	***		•••	5	• • • •	5
Furnace-bottom wasted	•••			•••	3	3
Furnaces bulged	• • •	• • •		2	7	9
Furnace-crown wasted	• • •		• • • •		6	6
Furnace grooved on top		• • •			1	1
Furnace grooved under bottom at	seams		• • •	• • •	1	1
Furnace much pitted	•••	•••	•••	• • •	1	1
Furnace wasted at back end Furnace wasted round door	• • •	•••			1	1
Furnace wasted round door Furnaces weak (strengthened)	•••	•••	•••	•••	$egin{array}{c} 1 \ 2 \end{array}$	1
Furnaces weak (pressure reduced)	•••				3	$\frac{2}{3}$
General decay, rivet-heads wasted				•••	5	5 5
General deterioration (pressure red				•••	164	164
Girders on firebox-crown wasted					4	4
Girder-stays defective				•••	i	1
Grooved at bottom of firebox	•••	•••		•••	3	3
Grooved at end of furnace				•••	3	3
Grooved at front end of boiler	• • •	•••			2	$\overset{\circ}{2}$
Grooved at landings		•••	• • •		2	2
Grooved on furnace-crown	• • •	•••		•••	1	1
Gusset-stays defective	•••	•••	•••	•••	1	1
Handhole door-openings wasted	•••	• • •	• • •		3	3
Header cap-bolts bad	•••	• • •	• • • •		1	1
Heads of stays in firebox wasted	•••	•••	• • •	•••	4	4
Laminated plate in furnace	•••	• • •	• • •	•••	2	2
Leaky seams	ilor	•••	• • •	• • •	4	4
Leaky stay-nuts at back end of bo		• • •	•••	•••	1	1
Longitudinal stays wasted	•••	•••	•••	•••	$egin{array}{cccccccccccccccccccccccccccccccccccc$	8
Lum-leg thin (pressure reduced) Manhole-doors bad			• • • •	•••	14	$\begin{array}{c} 1 \\ 14 \end{array}$
Manhole-doors riveting bad	•••			• • •	5	5
Manhole-door spigots defective	•••			•••	3	3
				•••	**	J