

OTI MATAURA COAL-SEAM.

Scale, 1 in.

ANALYSIS.

	Ash.	Fixed Carbon.	Volatile Hydro- carbons.	Water.	Coke.	Sulphur.
12 in. coal and black clay						
16 in. good coal ..	5.3	55.0	37.2	2.45	60.3	0.496
7 in. yellow stone band						
4 in. splint coal ..						
7 in. good coal ..	6.0	52.8	39.5	1.60	58.8	0.510
5 in. black stony coal						
9 in. good coal ..	8.4	52.6	37.4	1.55	61.0	0.521
11 in. black stone ..						
27 in. good coal ..	7.8	53.8	36.9	1.45	61.6	0.603

(Sampled 75 ft. in drive.)